

SAFE CURE & SEAL™ (J-18)

WATER BASED CURE, SEAL AND DUSTPROOFER V.O.C. COMPLIANT.

PRODUCT DESCRIPTION:

Safe Cure & Seal is a water based acrylic copolymer containing 16% solids that offers a combination curing, sealing and dustproofing for freshly finished concrete surfaces. This product dries to produce a non-yellowing, durable, clear film on concrete. Safe Cure & Seal is ideal for interior applications because it is free of noxious flammable fumes.

PURPOSE:

Safe Cure & Seal is a convenient, safe-to-use product that meets the ASTM C-309 specs as an effective membrane curing compound and is an excellent dustproofer and surface sealer. It is designed for interior and exterior use on both freshly finished and older concrete surfaces.

Because it is water based, Safe Cure & Seal is much safer to use than conventional solvent based products. Typically, solvent based products are flammable and have a strong irritating odor. Safe Cure & Seal has no odor and is non-flammable.

Safe Cure & Seal will resist many chemicals, help protect against staining and allows for easy removal of mortar splatters.

ADVANTAGES:

- Water based
- Meets ASTM C-309 Specs as an effective curing compound
- Excellent sealer & dustproofer
- Low odor
- Non-Flammable
- Easy clean-up with water
- Good chemical and stain resistance
- Interior/exterior applications

MEETS SPECIFICATIONS:

ASTM C-156 (Method of testing water retention for ASTM C-309)
ASTM C-309, Type 1, Class A & B,
AASHTO M-148, Type 1, Class A & B

Note: Federal Specification TT-C-800A has been cancelled and officially replaced by ASTM C-309.

APPLICATION INSTRUCTIONS:

Agitate Safe Cure & Seal before each use.

FRESH CONCRETE:

Apply Safe Cure & Seal immediately after all surface water has disappeared and the surface cannot be marred. Application of Safe Cure & Seal too early or too late can affect the overall curing performance. Use low pressure spray, roller or brush. Do not thin. Apply uniformly without puddles.

Application of a second coat, after the first coat has dried, will provide a longer lasting, higher gloss coating with improved water retention performance.

Old Concrete:

Clean and restore surface as required. Apply two uniform applications as above. Allow first coat to dry before applying second coat.

Note: On old concrete surfaces, Dayton Superior recommends a more breathable sealer like: Safe Seal Heavy Duty (J-24 H.D.) or Day-Chem Tuf Seal (J-35).

APPROXIMATE COVERAGE RATES:

	FT ² per Gallon	M ² per Liter
Curing	200	4.9
Sealing	200 – 400	4.9 – 9.8
Second Coat	400 – 600	9.8 – 14.7

Texture and absorption of surface will influence final coverage rates.

DRYING TIME:

Approx. 2-3 hrs. at 70°F (21°C). for recoating or light traffic. Wait 12 hrs. for heavy traffic. Dry time is temperature and humidity dependent.

PACKAGING:

5 gal. (18.9L) pails and 55 gal. (208L) drums

CLEANUP:

Tools and equipment can be cleaned with warm, soapy water before the product dries. For removal of dried product, use Dayton Superior Citrus Peel (J-48).

LIMITATIONS:

This product should not be used at temps. below 40°F (4°C). Do not apply concrete or mortar toppings over sealed surfaces.

Refer to www.daytonsuperior.com for latest Technical Data Sheet and MSDS
7777 Washington Village Dr., Suite 130, Dayton OH 45459
Customer Service: (888) 977-9600
Technical Assistance: (866) 329-8724

04/05 • For Commercial/Industrial Use Only • Page 1 of 2

5-7

SAFE CURE & SEAL™ (J-18)

Remove Safe Cure & Seal with Citrus Peel (J-48) before applying resinous (epoxy, polyester, urethane, etc.) coatings. May show rubber tire marks.

Do not allow the stored product to freeze. Shelf life is one year.

WARNING:

Use with adequate ventilation
Keep out of the reach of children
Do not take internally
In case of ingestion, CALL A PHYSICIAN immediately.
DO NOT induce vomiting

If splashed in the eyes, flush thoroughly with clean water for a minimum of 15 minutes. CALL A PHYSICIAN immediately. May cause irritation to the skin. If brought into contact with the skin, wash thoroughly with soap and water. Avoid excessive breathing of vapors and spray mist. Reseal container after each use. Wear protective clothing, gloves, and goggles. Read MSDS before using product.

MANUFACTUROR

Dayton Superior Corporation
7777 Washington Village Dr., Ste. 130
Dayton, OH 45459
Customer Service: 877-977-9600
Technical Services: 866-329-8724
Website: www.daytonsuperior.com

WARRANTY

Dayton Superior Corporation ("Dayton") warrants for 12 months from the date of manufacture or for the duration of the published product shelf life, whichever is less, that at the time of shipment by Dayton, the product is free of manufacturing defects and conforms to Dayton's product properties in force on the date of acceptance by Dayton of the order. Dayton shall only be liable under this warranty if the product has been applied, used, and stored in accordance with Dayton's instructions, especially surface preparation and installation, in force on the date of acceptance by Dayton of the order. The purchaser must examine the product when received and promptly notify Dayton in writing of any non-conformity before the product is used and no later than 30 days after such non-conformity is first discovered. If Dayton, in its sole discretion, determines that the product breached the above warranty, it will, in its sole discretion, replace the non-conforming product, refund the purchase price or issue a credit in the amount of the purchase price. This is the sole and exclusive remedy for breach of this warranty. Only a Dayton officer is authorized to modify this warranty. The information in this data sheet supersedes all other sales information received by the customer during the sales process. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM, TRADE OR OTHERWISE.

LIMITATION OF LIABILITY

Dayton shall not be liable in contract or in tort (including, without limitation, negligence, strict liability or otherwise) for loss of sales, revenues or profits; cost of capital or funds; business interruption or cost of downtime, loss of use, damage to or loss of use of other property (real or personal); failure to realize expected savings; frustration of economic or business expectations; claims by third parties (other than for bodily injury), or economic losses of any kind; or for any special, incidental, indirect, consequential, punitive or exemplary damages arising in any way out of the performance of, or failure to perform, its obligations under any contract for sale of product, even if Dayton could foresee or has been advised of the possibility of such damages. The Parties expressly agree that these limitations on damages are allocations of risk constituting, in part, the consideration for this contract, and also that such limitations shall survive the determination of any court of competent jurisdiction that any remedy provided in these terms or available at law fails of its essential purpose.

