

SikaRepair® 222

One-component, early strength gaining,
cementitious patching material

Description	SikaRepair® 222 is a one-component, early strength gaining, cementitious, patching material for horizontal repair of concrete.
Where to Use	<ul style="list-style-type: none">■ On grade, above and below grade on concrete and mortar.■ As a repair material for spalled horizontal concrete surfaces, walkways, ramps, steps, etc.
Advantages	<ul style="list-style-type: none">■ Easy-to-use; just add water.■ Not a vapor barrier.■ Suitable for exterior and interior applications.■ Not flammable.■ Easily applied to clean, sound substrate.■ High early strengths.
Coverage	Approximately 0.42 cu. ft. Approximately 0.62 cu. ft. (222+32 lbs. of 3/8" pea gravel).
Packaging	50 lb. multi-wall bag. SikaLatex R - 1 gal. plastic jug; 4/carton, 5 gal. pails

Typical Data (Material and curing conditions @ 73°F (23°C) and 50% R.H.)

RESULTS MAY DIFFER BASED UPON STATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, TEMPERATURE, APPLICATION METHODS, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.

Shelf life	One year in original, unopened bags.
Storage Conditions	Store dry at 40°-95°F (4°-35°C). Condition material to 65°-75°F before using.
Color	Concrete gray
Mixing Ratio	gallon to gallon of liquid per 50 lb. bag
Application Time	Approximately 30 minutes
Finishing Time	50-120 minutes

Note: All times start after adding Component 'B' to Component 'A' and are highly affected by temperature, relative humidity, substrate temperature, wind, sun, and other jobsite conditions.

Compressive Strength (ASTM C109)

1 day	>2,000 psi (12.4 MPa)
7 days	4,000 psi (27.6 MPa)
28 days	5,000 psi (34.5 MPa)

With undiluted Latex R

2,300 psi (15.9 MPa)
4,500 psi (31.0 MPa)
5,500 psi

Flexural Strength (ASTM C293)

28 days	750 psi (5.2 MPa)	1,200 psi (8.2 MPa)
----------------	-------------------	---------------------

Splitting Tensile Strength (ASTM C496)

28 days	450 psi (3.1 MPa)	700 psi (4.8 MPa)
----------------	-------------------	-------------------

Bond Strength *(ASTM C882 modified)

28 days	2,000 psi (13.8 MPa)	2,000 psi (13.8 MPa)
----------------	----------------------	----------------------

* Mortar scrubbed into substrate.

Construction



PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.

How to Use

Surface Preparation Surface Preparation Remove all deteriorated concrete, dirt, oil grease and all bond inhibiting materials from surface. Preparation work should be done by high pressure water blast, scabber, or other appropriate mechanical means to obtain an exposed aggregate surface with a minimum surface profile of $\pm 1/8$ inch. (CSP-6). Saturate surface with clean water. Substrate should be saturated surface dry (SSD) with no standing water during application.

Priming

For priming of reinforcing steel use Sika® Armatec® 110 EpoCem (consult Technical Data Sheet). Concrete Substrate: Prime the prepared substrate with a brush or sprayed applied coat of Sika® Armatec® 110 EpoCem (consult Technical Data Sheet). Alternately, a scrub coat of SikaRepair® 222 can be applied prior to placement of the mortar. The repair mortar has to be applied into the wet scrub coat before it dries.

Mixing

With water: Wet down all tools and mixer to be used. Add approximately 3/4 gallon of water to mixing vessel. Slowly add 1 bag of SikaRepair® 222 while continuing to mix. Mechanically mix with a low-speed drill (400-600 rpm) and Sika paddle or in an appropriate size mortar mixer. Add an additional 1/8 gallon of water if needed. With Latex R: Pour 3/4 gallon of SikaLatex® R into the mixing container. Slowly add powder, mix and adjust as above.

With diluted Latex R: SikaLatex® R may be diluted up to 5:1 (water: Sika Latex R) for projects requiring minimal polymer-modification. Pour 3/4 gallon of the mixture into the mixing container. Slowly add powder, mix and adjust as above. SikaRepair® 222 Concrete: For applications greater than 1 inch depth, add a 3/8 inch coarse aggregate. Aggregate must be non-reactive (reference ASTM C1260, C227 and C289), clean, well-graded, saturated surface dry (SSD), have low absorption and high density, and comply with ASTM C33 size number 8 per Table 2. Addition rate must not exceed 32 lbs. of aggregate/bag of SikaRepair® 222 (32 lbs. of 3/8 in. aggregate is approximately 2.5 to 3.0 gal. by loose volume of aggregate). Water may be varied to achieve the desired consistency. Do not over water.

Application

The prepared mortar must be scrubbed into the substrate, filling all pores and voids. Force material against edge of repair, working toward center. After filling repair, consolidate, then screed. Allow mortar to set to desired stiffness, then finish. Mixing, placing and finishing should not exceed 45 minutes maximum.

Tooling & Finishing

Curing As per ACI recommendations for portland cement concrete, curing is required. Moist cure with wet burlap and polyethylene, a fine mist of water or a water based, compatible curing compound. Curing compounds adversely affect the adhesion of following lifts of mortar, leveling mortar or protective coatings. Moist curing should commence immediately after finishing. Protect freshly applied mortar from direct sunlight, wind, rain and frost.

Limitations

- Application thickness: (with water and diluted Latex R) Min. Max. inches one lift Neat 1/4 inch (6 mm) 1 inch (25 mm) Extended 1 inch (25 mm) 4 inches (100 mm)
- Application thickness: (with undiluted Latex R) Min. Max. inches one lift Neat 1/8 in (3 mm) 1 inch (25 mm) Extended 1 inch (25 mm) 4 inches (100 mm)
- Minimum ambient and surface temperatures 45°F (7°C) and rising at time of application.
- Addition of coarse aggregates may result in variations of the physical properties of the mortar.
- Use only potable water.
- Not intended for use as an overlay material.
- As with all cement based materials, avoid contact with aluminum to prevent adverse chemical reaction and possible product failure. Insulate potential areas of contact by coating aluminum bars, rails, posts etc. with an appropriate epoxy such as Sikadur® Hi-Mod 32.

PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.

KEEP CONTAINER TIGHTLY CLOSED. KEEP OUT OF REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION. FOR INDUSTRIAL USE ONLY. FOR PROFESSIONAL USE ONLY.

For further information and advice regarding transportation, handling, storage and disposal of chemical products, users should refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety related data. Read the current actual Safety Data Sheet before using the product. In case of emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Product Data Sheet, product label and Safety Data Sheet which are available online at <http://usa.sika.com/> or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Product Data Sheet, product label and Safety Data Sheet prior to product use.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. SALE OF SIKA PRODUCTS ARE SUBJECT SIKA'S TERMS AND CONDITIONS OF SALE AVAILABLE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING 201-933-8800.

Visit our website at usa.sika.com

1-800-933-SIKA NATIONWIDE

Regional Information and Sales Centers. For the location of your nearest Sika sales office, contact your regional center.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Sika, SikaRepair, and SikaLatex are registered trademarks. Printed in Canada.

